NEWZEN CONSULTANTS BANGALORE

NEW TECHNOLOGIES TO INNOVATE

Date: 28-12-2020

NC/QC/VPD/2020-21/SB/W5-1-CB7A

## 1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength)
[Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No. 05.]

Ref. Material testing/PMC/20-21.

Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.

Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

## RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

### CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : $M_{20}$

TABLE 1.1:

| Sl No | Location/ Identification* | Date of Casting* | Date of Testing | Age in Days | C/S Area in $mm^2$ | Maximum Load in K.N | Compressive Strength ($N/mm^2$) | Avg. Value |
|---|---|---|---|---|---|---|---|---|
| 1 | 001 | 30-11-20 | 28-12-20 | 28 | 22500 | 500 | 22.22 | 22.44 |
| | 002 | " | " | " | " | 510 | 22.67 | |
| | 003 | " | " | " | " | 505 | 22.44 | |

The result of the materials tested meets the standards and hence can be used for the work.

Sample Collected Site : Vinayakanagara



NEWZEN CONSULTANT BANGALORE

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

Date: 28-12-2020

NC/QC/YPD/2020-21/SB/W5-1-CB8A

## 1. TEST REPORT ON CEMENT CONCRETE CUBES:

**Sub**: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
**Ref.**: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

### RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

### CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : $M_{20}$

**TABLE 1.1:**

| Sl No | Location/ Identification* | Date of Casting* | Date of Testing | Age in Days | C/S Area in $mm^2$ | Maximum Load in K.N | Compressive Strength ($N/mm^2$) | Avg. Value |
|---|---|---|---|---|---|---|---|---|
| 1 | 001 | 30-11-20 | 28-12-20 | 28 | 22500 | 495 | 22.00 | **22.22** |
| | 002 | " | " | " | " | 500 | 22.22 | |
| | 003 | " | " | " | " | 505 | 22.44 | |

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Vinayakanagara.



NEWZEN CONSULTANT

Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB9A

Date: 28-12-2020

## 1. TEST REPORT ON CEMENT CONCRETE CUBES:

**Sub**: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
**Ref.**: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

### RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

### CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : $M_{20}$

**TABLE 1.1:**

| Sl No | Location/ Identification* | Date of Casting* | Date of Testing | Age in Days | C/S Area in $mm^2$ | Maximum Load in K.N | Compressive Strength ($N/mm^2$) | Avg. Value |
|---|---|---|---|---|---|---|---|---|
| 1 | 001 | 30-11-20 | 28-12-20 | 28 | 22500 | 515 | 22.89 | **22.89** |
| | 002 | " | " | " | " | 510 | 22.67 | |
| | 003 | " | " | " | " | 520 | 23.11 | |

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Vinayakanagara.



NEWZEN CONSULTANT

Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/VPD/2020-21/SB/W5-1-CB10A Date: 29-12-2020

## I. TEST REPORT ON CEMENT CONCRETE CUBES:

**Sub**: Testing of Concrete Cubes (for 28days Compressive Strength)
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05 }
**Ref.**: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

### RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

### CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : $M_{20}$

**TABLE 1.1:**

| Sl No | Location/ Identification* | Date of Casting* | Date of Testing | Age in Days | C/S Area in $mm^2$ | Maximum Load in K.N | Compressive Strength ($N/mm^2$) | Avg. Value |
|---|---|---|---|---|---|---|---|---|
| 1 | 001 | 01-12-20 | 29-12-20 | 28 | 22500 | 505 | 22.44 | **22.81** |
| | 002 | " | " | " | " | 520 | 23.11 | |
| | 003 | " | " | " | " | 515 | 22.89 | |

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Vinayakanagara.



NEWZEN CONSULTANT BANGALORE

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB11A Date: 29-12-2020

## 1. TEST REPORT ON CEMENT CONCRETE CUBES:

**Sub**: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
**Ref.**: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

### RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

### CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : $M_{20}$

**TABLE 1.1:**

| Sl No | Location/ Identification* | Date of Casting* | Date of Testing | Age in Days | C/S Area in $mm^2$ | Maximum Load in K.N | Compressive Strength ($N/mm^2$) | Avg. Value |
|---|---|---|---|---|---|---|---|---|
| 1 | 001 | 01-12-20 | 29-12-20 | 28 | 22500 | 515 | 22.89 | **22.59** |
| | 002 | " | " | " | " | 500 | 22.22 | |
| | 003 | " | " | " | " | 510 | 22.67 | |

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Vinayakanagara.



NEWZEN CONSULTANT

Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NCQC\PD\2020-21\SB\WS-I-CB12A

Date: 29-12-2020

## I. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength)

(Project* Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05 )

Ref.: Material testing/PMC/20-21.

Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.

Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

### RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

### CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : $M_{30}$

**TABLE 1.1:**

| Sl No | Location/ Identification* | Date of Casting* | Date of Testing | Age in Days | C/S Area in $mm^2$ | Maximum Load in K.N | Compressive Strength ($N/mm^2$) | Avg. Value |
|---|---|---|---|---|---|---|---|---|
| 1 | 001 | 01-12-20 | 29-12-20 | 28 | 22500 | 515 | 22.89 | 22.52 |
| | 002 | " | " | " | " | 495 | 22.00 | |
| | 003 | " | " | " | " | 510 | 22.67 | |

The result of the materials tested meets the standards and hence can be used for the work.

Sample Collected Site : Vinayakanagara.



NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAIYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB13A Date: 30-12-2020

## 1. TEST REPORT ON CEMENT CONCRETE CUBES:

**Sub**: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
**Ref.**: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

### RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

### CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : $M_{20}$

**TABLE 1.1:**

| Sl No | Location/ Identification* | Date of Casting* | Date of Testing | Age in Days | C/S Area in $mm^2$ | Maximum Load in K.N | Compressive Strength ($N/mm^2$) | Avg. Value |
|---|---|---|---|---|---|---|---|---|
| 1 | 001 | 02-12-20 | 30-12-20 | 28 | 22500 | 510 | 22.67 | **22.37** |
| | 002 | " | " | " | " | 495 | 22.00 | |
| | 003 | " | " | " | " | 505 | 22.44 | |

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.



NEWZEN CONSULTANT

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/VPD/2020-21/SB/W5-1-CB14A

Date: 30-12-2020

## 1. TEST REPORT ON CEMENT CONCRETE CUBES:

**Sub**: Testing of Concrete Cubes (for 28days Compressive Strength)
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05 }
**Ref.**: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

### RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

### CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : $M_{20}$

**TABLE 1.1:**

| Sl No | Location/ Identification* | Date of Casting* | Date of Testing | Age in Days | C/S Area in $mm^2$ | Maximum Load in K.N | Compressive Strength ($N/mm^2$) | Avg. Value |
|---|---|---|---|---|---|---|---|---|
| 1 | 001 | 02-12-20 | 30-12-20 | 28 | 22500 | 525 | 23.33 | **22.96** |
| | 002 | " | " | " | " | 515 | 22.89 | |
| | 003 | " | " | " | " | 510 | 22.67 | |

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.



NEWZEN CONSULTANT BANGALORE

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB15A

Date: 30-12-2020

## 1. TEST REPORT ON CEMENT CONCRETE CUBES:

**Sub**: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
**Ref.**: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

### RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

### CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : $M_{20}$

**TABLE 1.1:**

| Sl No | Location/ Identification* | Date of Casting* | Date of Testing | Age in Days | C/S Area in $mm^2$ | Maximum Load in K.N | Compressive Strength ($N/mm^2$) | Avg. Value |
|---|---|---|---|---|---|---|---|---|
| 1 | 001 | 02-12-20 | 30-12-20 | 28 | 22500 | 520 | 23.11 | **22.74** |
| | 002 | " | " | " | " | 510 | 22.67 | |
| | 003 | " | " | " | " | 505 | 22.44 | |



NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB16A

Date: 31-12-2020

## 1. TEST REPORT ON CEMENT CONCRETE CUBES:

**Sub**: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
**Ref.**: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

### RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

### CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : $M_{20}$

**TABLE 1.1:**

| Sl No | Location/ Identification* | Date of Casting* | Date of Testing | Age in Days | C/S Area in $mm^2$ | Maximum Load in K.N | Compressive Strength ($N/mm^2$) | Avg. Value |
|---|---|---|---|---|---|---|---|---|
| 1 | 001 | 03-12-20 | 31-12-20 | 28 | 22500 | 500 | 22.22 | **22.44** |
| | 002 | " | " | " | " | 510 | 22.67 | |
| | 003 | " | " | " | " | 505 | 22.44 | |

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.



NEWZEN CONSULTANT BANGALORE

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB17A Date: 31-12-2020

## 1. TEST REPORT ON CEMENT CONCRETE CUBES:

**Sub**: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
**Ref.**: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

### RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

### CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : $M_{20}$

**TABLE 1.1:**

| Sl No | Location/ Identification* | Date of Casting* | Date of Testing | Age in Days | C/S Area in $mm^2$ | Maximum Load in K.N | Compressive Strength ($N/mm^2$) | Avg. Value |
|---|---|---|---|---|---|---|---|---|
| 1 | 001 | 03-12-20 | 31-12-20 | 28 | 22500 | 495 | 22.00 | **22.22** |
| | 002 | " | " | " | " | 500 | 22.22 | |
| | 003 | " | " | " | " | 505 | 22.44 | |

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.



NEWZEN CONSULTANT Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB18A

Date: 31-12-2020

## 1. TEST REPORT ON CEMENT CONCRETE CUBES:

**Sub**: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
**Ref.**: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

### RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

### CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : $M_{20}$

**TABLE 1.1:**

| Sl No | Location/ Identification* | Date of Casting* | Date of Testing | Age in Days | C/S Area in $mm^2$ | Maximum Load in K.N | Compressive Strength ($N/mm^2$) | Avg. Value |
|---|---|---|---|---|---|---|---|---|
| 1 | 001 | 03-12-20 | 31-12-20 | 28 | 22500 | 515 | 22.89 | **22.89** |
| | 002 | " | " | " | " | 510 | 22.67 | |
| | 003 | " | " | " | " | 520 | 23.11 | |

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.



NEWZEN CONSULTANT BANGALORE

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB19A

Date: 01-01-2021

## 1. TEST REPORT ON CEMENT CONCRETE CUBES:

**Sub**: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
**Ref.**: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

### RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

### CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : $M_{20}$

**TABLE 1.1:**

| Sl No | Location/ Identification* | Date of Casting* | Date of Testing | Age in Days | C/S Area in $mm^2$ | Maximum Load in K.N | Compressive Strength ($N/mm^2$) | Avg. Value |
|---|---|---|---|---|---|---|---|---|
| 1 | 001 | 04-12-20 | 01-01-21 | 28 | 22500 | 515 | 22.89 | **22.59** |
| | 002 | " | " | " | " | 500 | 22.22 | |
| | 003 | " | " | " | " | 510 | 22.67 | |

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.



NEWZEN CONSULTANT Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB20A

Date: 01-01-2021

## 1. TEST REPORT ON CEMENT CONCRETE CUBES:

**Sub**: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}

**Ref.**: Material testing/PMC/20-21,

Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.

Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

## RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

### CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : $M_{20}$

**TABLE 1.1:**

| Sl No | Location/ Identification* | Date of Casting* | Date of Testing | Age in Days | C/S Area in $mm^2$ | Maximum Load in K.N | Compressive Strength ($N/mm^2$) | Avg. Value |
|---|---|---|---|---|---|---|---|---|
| 1 | 001 | 04-12-20 | 01-01-21 | 28 | 22500 | 515 | 22.89 | **22.52** |
| | 002 | " | " | " | " | 495 | 22.00 | |
| | 003 | " | " | " | " | 510 | 22.67 | |

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.

NEWZEN CONSULTANT Bangalore



NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB21A

Date: 01-01-2021

## 1. TEST REPORT ON CEMENT CONCRETE CUBES:

**Sub**: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
**Ref.**: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

## RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

### CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : $M_{20}$

**TABLE 1.1:**

| Sl No | Location/ Identification* | Date of Casting* | Date of Testing | Age in Days | C/S Area in $mm^2$ | Maximum Load in K.N | Compressive Strength ($N/mm^2$) | Avg. Value |
|---|---|---|---|---|---|---|---|---|
| 1 | 001 | 04-12-20 | 01-01-21 | 28 | 22500 | 510 | 22.67 | **22.37** |
| | 002 | " | " | " | " | 495 | 22.00 | |
| | 003 | " | " | " | " | 505 | 22.44 | |

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.



NEWZEN CONSULTANT Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB22A

Date: 04-01-2021

## 1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
(Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.)
Ref: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

## RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

### CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : $M_{20}$

**TABLE 1.1:**

| Sl No | Location/ Identification* | Date of Casting* | Date of Testing | Age in Days | C/S Area in $mm^2$ | Maximum Load in K.N | Compressive Strength ($N/mm^2$) | Avg. Value |
|---|---|---|---|---|---|---|---|---|
| 1 | 001 | 07-12-20 | 04-01-21 | 28 | 22500 | 525 | 23.33 | 22.96 |
| | 002 | " | " | " | " | 515 | 22.89 | |
| | 003 | " | " | " | " | 510 | 22.67 | |

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.



NEWZEN CONSULTANT Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB23A

Date: 04-01-2021

## 1. TEST REPORT ON CEMENT CONCRETE CUBES:

**Sub**: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
**Ref.**: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

### RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

### CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : $M_{20}$

**TABLE 1.1:**

| Sl No | Location/ Identification* | Date of Casting* | Date of Testing | Age in Days | C/S Area in $mm^2$ | Maximum Load in K.N | Compressive Strength ($N/mm^2$) | Avg. Value |
|---|---|---|---|---|---|---|---|---|
| 1 | 001 | 07-12-20 | 04-01-21 | 28 | 22500 | 520 | 23.11 | **22.74** |
| | 002 | " | " | " | " | 510 | 22.67 | |
| | 003 | " | " | " | " | 505 | 22.44 | |

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.



NEWZEN CONSULTANT * Bangalore *

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB24A

Date: 04-01-2021

## 1. TEST REPORT ON CEMENT CONCRETE CUBES:

**Sub**: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
**Ref.**: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

### RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

### CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : $M_{20}$

**TABLE 1.1:**

| Sl No | Location/ Identification* | Date of Casting* | Date of Testing | Age in Days | C/S Area in $mm^2$ | Maximum Load in K.N | Compressive Strength ($N/mm^2$) | Avg. Value |
|---|---|---|---|---|---|---|---|---|
| 1 | 001 | 07-12-20 | 04-01-21 | 28 | 22500 | 500 | 22.22 | **22.44** |
| | 002 | " | " | " | " | 510 | 22.67 | |
| | 003 | " | " | " | " | 505 | 22.44 | |

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.



NEWZEN CONSULTANT Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner